

NOMENCLATURE OF THE MICAS

MILAN RIEDER,¹ GIANCARLO CAVAZZINI,² YURII S. D'YAKONOV,³ VIKTOR A. FRANK-KAMENETSKII,[†]
 GLAUCO GOTTARDI,[‡] STEPHEN GUGGENHEIM,⁴ PAVEL V. KOVAL,⁵ GEORG MÜLLER,⁶ ANA M. R. NEIVA,⁷
 EDWARD W. RADOSLOVICH,[§] JEAN-LOUIS ROBERT,⁸ FRANCESCO P. SASSI,² HIROSHI TAKEDA,⁹
 ZDENĚK WEISS¹⁰ AND DAVID R. WONES[¶]

¹ Department of Geochemistry, Mineralogy and Mineral Resources, Charles University, Albertov 6,
 128 43 Praha 2, Czech Republic

² Dipartimento di Mineralogia e Petrologia, Università di Padova, Corso Garibaldi, 37, I-35122 Padova, Italy
³ VSEGEI, Srednii pr., 74, 199 026 Sankt-Peterburg, Russia

⁴ Department of Geological Sciences, University of Illinois at Chicago, 845 West Taylor St.,
 Chicago, Illinois 60607-7059, USA

⁵ Institut geokhimii SO AN Rossii, ul. Favorskogo 1 a, Irkutsk-33, Russia 664 033

⁶ Institut für Mineralogie und Mineralische Rohstoffe, Technische Universität Clausthal, Postfach 1253,
 D-38670 Clausthal-Zellerfeld, Germany

⁷ Departamento de Ciências da Terra, Universidade de Coimbra, Apartado 3014, 3049 Coimbra CODEX, Portugal

⁸ Centre de Recherche sur la Synthèse et la Chimie des Minéraux, C.N.R.S., 1A, Rue de la Férollerie,
 45071 Orléans CEDEX 2, France

⁹ Chiba Institute of Technology, 2-17-1 Tsudanuma, Narashino City, Chiba 275, Japan


¹⁰ Central Analytical Laboratory, Technical University of Mining and Metallurgy, Tř.17.listopadu,
 708 33 Ostrava-Poruba, Czech Republic

Abstract—End members and species defined with permissible ranges of composition are presented for the true micas, the brittle micas and the interlayer-cation-deficient micas. The determination of the crystallochemical formula for different available chemical data is outlined, and a system of modifiers and suffixes is given to allow the expression of unusual chemical substitutions or polytypic stacking arrangements. Tables of mica synonyms, varieties, ill-defined materials and a list of names formerly or erroneously used for micas are presented. The Mica Subcommittee was appointed by the Commission on New Minerals and Mineral Names (“Commission”) of the International Mineralogical Association (IMA). The definitions and recommendations presented were approved by the Commission.

Key Words—Mica, Nomenclature.

DEFINITION

Micas are phyllosilicates in which the unit structure consists of 1 octahedral sheet (Os) between 2 opposing tetrahedral sheets (Ts). These sheets form a layer that is separated from adjacent layers by planes of nonhydrated interlayer cations (I). The sequence is . . . I Ts Os Ts I Ts Os . . . The tetrahedral sheets have composition T₂O₅, and tetrahedra are linked by sharing each of 3 corners (= basal atoms of oxygen) to a neighboring tetrahedron; the 4th corner (= apical atom of oxygen) points in one direction for a given tetrahedral sheet. The coordinating anions around octahedral cations (M) consist of apical atoms of oxygen of adjacent tetrahedral sheets and anions (A). The coordination of interlayer cations is nominally 12-fold, and their charge should not be less than 0.6 per formula. The simplified formula can be written as:



where:

I is commonly **Cs, K, Na, NH₄, Rb, Ba, Ca**

M is commonly **Li, Fe^{II} or Fe^{III}, Mg, Mn^{II} or Mn^{III}, Zn, Al, Cr, V, Ti**

□ is vacancy

T is commonly **Be, Al, B, Fe^{III}, Si**

A is commonly **Cl, F, OH, O (oxy-micas), S**

(most frequently encountered elements are set in boldface; note that other substitutions are possible). The number of formula units, Z, may vary depending on the structure, but is equal to 2 in a 1M structure.

SUBDIVISIONS

Depending on the interlayer cation, the micas are subdivided into true micas (if ≥50% I cations present are univalent) and brittle micas (if >50% I cations present are divalent). If the formula exhibits <0.85 and ≥0.6 positive interlayer charges, it represents an

[†] Russia; died 1994.

[‡] Italy; died 1988.

[§] Australia; resigned 1986.

[¶] U.S.A.; died 1984.

interlayer-cation-deficient mica or, in an abbreviated form, an interlayer-deficient mica. In special cases (such as wonesite), the interlayer charge may be lower than 0.6 provided the material does not have swelling or expanding capabilities. The 0.85 charge threshold holds for dioctahedral micas. To date, there are insufficient data to define an analogous limit in trioctahedral micas.

Regardless of the mica subgroup, it is dioctahedral if it contains <2.5 octahedral cations (M) per formula unit; micas with ≥ 2.5 octahedral cations are trioctahedral. Micas with intermediate octahedral occupancies occur frequently, but no provision is made for any other divisions or terms (for example, “ $2\frac{1}{2}$ octahedral”); the use of such terms is discouraged. Also discouraged is the division of micas into “disilicic”, “trisilicic” and “tetrasilicic” according to the number of Si atoms per formula.

Octahedrally coordinated M cations may be distributed over 3 crystallographic positions (octahedral ordering) or 2 positions in structures with the $C2/m$ space group. Because of this ordering, some end-member formulas do not conform to the “chemical” 50% rule of Nickel (1992). To a lesser extent, the same applies to tetrahedrally coordinated T cations.

PRINCIPLES OF CLASSIFICATION

The present classification is based on the chemical composition of micas and embodies generalizations derived from crystal-structure determinations. The inclusion of physical determinative properties as classification criteria was avoided because these properties cannot unambiguously differentiate members of the micas. Moreover, the approach adopted here reflects the belief that mica classification should be based on easily accessible chemical data and a minimum of physical measurements.

The crystallochemical formula should be based on chemical analysis, density and cell data. If chemical data only are available, the recommended procedure to calculate a formula is as follows: 1) If there is a reliable determination of H_2O , the formula should be based on 12 O + F atoms. 2) If there is no determination of H_2O , as in microprobe analyses, an idealized anion group must be assumed, and the formula should be based on 22 positive charges. 3) If there is no determination of H_2O and there are grounds to suspect that a *later* oxidation of Fe in the mica caused deprotonation of the anion group, the formula should be based on $22 + z$ positive charges, where z is the quantity of Fe(III) (Stevens 1946; Foster 1960; Rimsaite 1970). It should be noted that Li, concentrations of which cannot be determined with current electron microprobe techniques, is commonly overlooked in wet-chemical analyses because of its low molecular weight. Also, failure to

establish the concentration of Li has caused a number of erroneous identifications.

END MEMBERS

End-member names given below are associated with formulas containing the most frequently encountered A anion only. End members in which other A anions dominate should be designated with the prefixes “fluoro” (for example, in muscovite), “hydroxy” (for example, in polyolithionite) or “oxy” (for example, in annite). When such phases are found in nature, their proposed new mineral status and name should nonetheless be submitted for approval to the Commission.

This report contains end-member formulas that are stoichiometric on the scale of the asymmetric part of the unit cell. Those mica species that do not meet this requirement (such as those in which the main end members are not yet clear) appear as “species that are not end members”. To express chemical variation in compositional plots, hypothetical end members may be employed. However, because these end members have not been documented as mineral species, they may not receive mineral-like names, and only formulas or formula-like expressions should be used in such plots. Experimental determinations of miscibility limits in natural mica series will help in establishing species and in positioning boundaries between them.

Lists of valid names for true, brittle and interlayer-deficient micas appear in Tables 1, 2 and 3, respectively. Compositional space for some dioctahedral interlayer-deficient and true micas is shown in Figure 1.

MODIFIERS AND SUFFIXES

Chemical deviations from end-member compositions may be expressed by adjectival modifiers. These must be based on actual determinations to support the claim. The usage of adjectival modifiers is not mandatory. Modifiers like “rubidian” should be used only if the element in question exceeds 10%, but not 50%, of the real occupancy of the respective position in the end-member formulas involved. Thus, a rubidian muscovite may contain between 0.1 and 0.5 Rb atoms per formula unit. If an element can enter more than 1 coordination, a further differentiation is possible, such as “tetra-ferrian” or “octa-ferrian”. If the concentration of an element is less than that necessary for the assignment of a modifier and the author wishes to acknowledge its presence, it may be done by using a modifier such as “rubidium-containing”. The latter type of modifier should be used also if the analysis is incomplete, thus preventing the calculation of a complete crystallochemical formula.

For cases where a polytype determination has been made, the name may be suffixed with an appropriate

Table 1. True micas: end-member formulas and typical ranges for mineral species.

	Di octahedral
muscovite	$K Al_2 \square AlSi_3 O_{10}(OH)_2$ $^{iv}Si: 3.0-3.1$ $^{vi}Al: 1.9-2.0$ K: 0.7-1.0 ($I \geq 0.85$) $^{vi}R^{II}/(^{vi}R^{II} + ^{vi}R^{III}) < 0.25$ $^{vi}Al/(^{vi}Al + ^{vi}Fe^{III}): 0.5-1.0$
aluminoceladonite	$K Al(Mg, Fe^{II}) \square Si_4 O_{10}(OH)_2$ $^{vi}R^{II}/(^{vi}R^{II} + ^{vi}R^{III}) \geq 0.25$ $^{vi}Al/(^{vi}Al + ^{vi}Fe^{III}): 0.5-1.0$ $Mg/(Mg + ^{vi}Fe^{II}) > 0.5$
ferro-aluminoceladonite	$K Al(Fe^{II}, Mg) \square Si_4 O_{10}(OH)_2$ $^{vi}Al/(^{vi}Al + ^{vi}Fe^{III}): 0.5-1.0$ $Mg/(Mg + ^{vi}Fe^{II}) \leq 0.5$
celadonite	$K Fe^{III}(Mg, Fe^{II}) \square Si_4 O_{10}(OH)_2$ $^{vi}R^{II}/(^{vi}R^{II} + ^{vi}R^{III}) \geq 0.25$ $^{vi}Al/(^{vi}Al + ^{vi}Fe^{III}) < 0.5$ $Mg/(Mg + ^{vi}Fe^{II}) > 0.5$
ferroceladonite	$K Fe^{III}(Fe^{II}, Mg) \square Si_4 O_{10}(OH)_2$ $^{vi}Al/(^{vi}Al + ^{vi}Fe^{III}) < 0.5$ $Mg/(Mg + ^{vi}Fe^{II}) \leq 0.5$
roscoelite	$K V_2 \square AlSi_3 O_{10}(OH)_2$
chromphyllite	$K Cr_2 \square AlSi_3 O_{10}(OH, F)_2$
boromuscovite	$K Al_2 \square BSi_3 O_{10}(OH)_2$
paragonite	$Na Al_3 \square AlSi_3 O_{10}(OH)_2$ K < 0.15 Ca < 0.11
nanpingite	$Cs Al_2 \square AlSi_3 O_{10}(OH)_2$
tobelite	$(NH_4) Al_2 \square AlSi_3 O_{10}(OH)_2$
	Tri octahedral
annite	$K Fe^{II} AlSi_3 O_{10}(OH)_2$
phlogopite	$K Mg_3 AlSi_3 O_{10}(OH)_2$
siderophyllite	$K Fe^{II} Al Al_2 Si_2 O_{10}(OH)_2$
eastonite	$K Mg_2 Al Al_2 Si_2 O_{10}(OH)_2$
hendricksite	$K Zn_3 AlSi_3 O_{10}(OH)_2$ Zn > 1.5
montdorite†	$K Fe^{II} Mn^{II} Mg_{0.5} \square_{0.5} Si_4 O_{10} F_2$ $Fe^{II} > Mn^{II} + Mg$
tainiolite	$K LiMg_2 Si_4 O_{10} F_2$
polyolithionite	$K Li_2 Al Si_4 O_{10} F_2$
trilithionite†	$K Li_{1.5} Al_{1.5} AlSi_3 O_{10} F_2$
masutomilite	$K LiAlMn^{II} AlSi_3 O_{10} F_2$ Mn ^{II} : 1.0-0.5 Li: 1.0-1.5 Si: 3.0-3.5 $^{iv}Al: 1.0-0.5$
norrishite	$K LiMn^{III} Si_4 O_{12}$
tetra-ferri-annite	$K Fe^{II} Fe^{III} Si_3 O_{10}(OH)_2$
tetra-ferriphlogopite	$K Mg_3 Fe^{III} Si_3 O_{10}(OH)_2$
aspidolite	$Na Mg_3 AlSi_3 O_{10}(OH)_2$
preiswerkite	$Na Mg_2 Al Al_2 Si_2 O_{10}(OH)_2$
ephesite	$Na LiAl_2 Al_2 Si_2 O_{10}(OH)_2$

† Species that are not end members.

polytype symbol (Nickel 1993), for example, muscovite-3T. There are 2 universal systems of polytype symbolism, both based on the modified Gard notation: one presented jointly by the IMA and the International Union of Crystallography (IUCr) (Bailey et al. 1977) and another, more generalized, by IUCr

Table 2. Brittle micas: end-member formulas and typical ranges for mineral species.

	Di octahedral
margarite	$Ca Al_2 \square Al_2 Si_2 O_{10}(OH)_2$ I = Ca, Na M = Al, Li, $\square > Li$ T = Al, Si, Be
chernykhite	$Ba V_2 \square Al_2 Si_2 O_{10}(OH)_2$ M: V, Al, Fe, Mg
	Tri octahedral
clintonite	$Ca Mg_2 Al Al_3 Si O_{10}(OH)_2$ I = Ca, Na, K M = Mg, Fe ^{II} , Al, Fe ^{III} , Mn T = Al, Si, Fe ^{III}
bityite	$Ca LiAl_2 BeAlSi_2 O_{10}(OH)_2$ $^{vi}Li > ^{vi}\square$
anandite	$Ba Fe^{II} Fe^{III} Si_3 O_{10} S(OH)$ I: Ba, K, Na M: Fe ^{II} , Mg, Fe ^{III} , Mn, Al A: S > OH, Cl, F
kinoshitalite	$Ba Mg_3 Al_2 Si_2 O_{10}(OH)_2$ I: Ba + K ~ 1.0 M: Mg, Mn ^{II} , Mn ^{III} , Al, Fe, Ti A: OH, F

(Guinier et al. 1984). Because of international acceptance and common usage, the Ramsdell symbolism is preferred for the micas unless exact stacking sequences or other special information need clarification; for the latter cases, see Ross et al. (1966), Takeda and Sadanaga (1969), Zvyagin (1964), Zvyagin et al. (1979) or Dornberger-Schiff and Đurovič (Đurovič 1981). When using the other systems or when using symbolism that is not commonly known, the

Table 3. Interlayer-deficient micas: representative formulas and ranges.

	Di octahedral†
Idealized general formula	$(K, Na)_x (Mg, Fe^{II})_x (Al, Fe^{III})_{2-x} \square_{0.5} Si_{4-x} (Al, Fe^{III})_y O_{10}(OH)_2$ $0.6 \leq x + y < 0.85$ Mg > Fe ^{II} $^{iv}Al > ^{iv}Fe^{III}$
illite (a series name)	$K_{0.65} Al_{2.0} \square Al_{0.65} Si_{3.35} O_{10}(OH)_2$ $^{vi}R^{II}/(^{vi}R^{II} + ^{vi}R^{III}) \leq 0.25$ $^{vi}Al/(^{vi}Al + ^{vi}Fe^{III}) \geq 0.6$
glauconite (a series name)	$K_{0.8} R_{1.33}^{II} R_{0.67}^{III} \square Al_{0.13} Si_{3.87} O_{10}(OH)_2$ $^{vi}R^{II}/(^{vi}R^{II} + ^{vi}R^{III}) \geq 0.15$ $^{vi}Al/(^{vi}Al + ^{vi}Fe^{III}) \leq 0.5$
brammallite (a series name)	$Na_{0.65} Al_{2.0} \square Al_{0.65} Si_{3.35} O_{10}(OH)_2$
	Tri octahedral
wonesite‡	$Na_{0.5} \square_{0.5} Mg_{2.5} Al_{0.5} AlSi_3 O_{10}(OH)_2$

† See also Figure 1; I = x + y.

‡ Species that is not an end member.




Figure 1. A 3-dimensional plot illustrating the relation of some true dioctahedral micas to interlayer-deficient dioctahedral micas. Figure (a) represents 2 slabs cut from the chemographic volume (b) shown in terms of formulas (small solid circles). Dashed lines indicate approximate borders; dotted lines complete the solid. The ratio ${}^{VI}R^{II}/({}^{VI}R^{II} + {}^{VI}R^{III})$ is equal to $x/2$ (Table 3) for micas with 2.0 octahedral cations. End-member formulas in drawing (a) are shown by solid circles. Glauconite with $Na > K$ should be referred to as "natroglauconite".

author must reference its source or, preferably, specify the stacking sequence represented by the symbols used. A review of polytypes in micas found to date can be found in Baronnet (1980), Bailey (1984) or Takeda and Ross (1995).

Table 4. Series names.

biotite	Trioctahedral micas between, or close to, the annite-phlogopite and siderophyllite-eastonite joins; dark micas without Li.
glauconite	Dioctahedral interlayer-deficient micas with composition defined in Table 3.
illite	Dioctahedral interlayer-deficient micas with composition defined in Table 3.
lepidolite	Trioctahedral micas on, or close to, the trilitionite-polyolithionite join; light micas with substantial Li.
phengite	Potassic dioctahedral micas between, or close to, the joins muscovite-aluminoceladonite and muscovite-celadonite.
zinnwaldite	Trioctahedral micas on, or close to, the siderophyllite-polyolithionite join; dark micas containing Li.

"Hendricksite", "chernykhite", "montdorite" and "masutomilite" should be added to these names if future research substantiates the existence of solid solutions terminated by 2 end members, such as $KZn_3AlSi_3O_{10}(OH)_2$ and $KMn_3^IIAlSi_3O_{10}(OH)_2$. The first of those, now listed as end member "hendricksite", should then be renamed to "zincohendricksite"; the second should become "manganohendricksite". The same pattern should apply in all cases given.

SERIES NAMES AND LISTS OF INVALID NAMES

This report also includes series names intended to designate incompletely investigated micas that are to be used by field geologists or petrographers (Table 4). Such names (for example, "biotite") are defined only in some series, thus in fact sanctioning a practice that is common already. Assigning a name to an incompletely investigated layer silicate may be risky, and it should be preceded by at least optical examination. Once such material has been studied in detail, end-member names should be preferred, with or without modifiers and suffixes. Series names are not to be associated with varietal modifiers.

Names whose usage is discouraged were divided into synonyms and varieties (Table 5), ill-defined materials and mixtures (Table 6) and names formerly or erroneously used for micas (Table 7).

JUSTIFICATION

This section summarizes grounds for some of the Mica Subcommittee's decisions.

Aluminoceladonite

The alternative term for this mica, "leucophyllite", was considered unjustified because it invites confusion with an identical rock-name and because the type-locality leucophyllite (Starkl 1883) is too low in alkalis to represent a mica.

Aspidolite

The Mica Subcommittee voted to resurrect the name "aspidolite" (von Kobell 1869), which rep-

Table 5. Synonyms (s) and varieties (v). Names in the left column should be abandoned in favor of those in the right. No symbol in parentheses indicates cases where it could not be decided whether it is a synonym or a variety.

adamsite	muscovite
alurgite (v)	manganoan muscovite, manganoan illite
ammochrysos	muscovite
ammonium hydromica (s)	tobelite
ammonium muscovite (s)	tobelite
amphilogite (s)	muscovite
anomite	biotite
astrolite (s)	muscovite
barium phlogopite (v)	phlogopite
barytbiotite (v)	phlogopite
biaxial mica	muscovite
bowleyite (s)	bityite
brandisite (v)	clintonite
bronzite (Finch) (v)	clintonite
caesium-biotite (v)	biotite
calcibiotite (v)	biotite
calciotalc (v)	clintonite
cat gold	muscovite
cat silver	muscovite
chacaltocite	muscovite
chlorophanerite	glaucosite
chrombiotite (v)	biotite
chrome mica (s)	chromian muscovite, chromian phengite
Chromglimmer (s)	chromian muscovite, chromian phengite
chromochre	chromian muscovite
chrysophane	clintonite
clingmanite (s)	margarite
colomite	roscoelite
common mica	muscovite
corundellite (s)	margarite
coossaite (v)	paragonite
cryophyllite (v)	zinnwaldite, ferroan trillithionite, ferroan polyolithionite
damourite	muscovite
didrimite	muscovite
didymite	muscovite
diphanite (s)	margarite
disterrite (v)	clintonite
dysintribite	muscovite
emerylite (s)	margarite
euchlorite (s)	biotite
ferrianite (s)	tetra-ferrite-annite
ferritbiotite (v)	biotite
ferrite-phengite (v)	ferrite muscovite
ferritephlogopite (v)	ferrite phlogopite, tetra-ferritephlogopite
ferrititanbiotite (v)	biotite
ferritewodianite (v)	biotite
ferritewotomite (v)	biotite
ferroferrite-margarite (v)	margarite
ferro-ferrite-muscovite (s)	ferrite annite
ferromuscovite (v)	biotite
ferro-phlogopite (v)	ferroan phlogopite
ferrophenlogopite (v)	ferroan phlogopite
flogopite (s)	phlogopite
fluortainiolite (s)	tainiolite
Frauenglas	muscovite
fuchsite	chromian muscovite
gaebhardtite†	chromian muscovite
gilbertite	muscovite
goeschwitzite	illite
grundite	illite
gümbellite	illite-2M ₂
haughtonite (v)	biotite
heterophyllite (v)	biotite
holmesite	clintonite
holmite	clintonite
hydromicas (s)	interlayer-deficient micas

Table 5. Continued.

hydromuscovite	illite
hydroparagonite (s)	brammallite
hydroxyl-annite (s)	annite
hydroxyl-biotite (s)	biotite
iron-sericite (v)	ferrian illite
iron mica‡	annite, siderophyllite, biotite
irvingite (v)	lithian muscovite
Isinglas	muscovite
Kaliglimmer	muscovite
killinite	illite
kmaite (s)	celadonite, ferrian celadonite
lepidomelane (v)	annite, siderophyllite, tetra-ferri-annite, biotite
lepidomorphite	phengite
leucophyllite (s)	aluminoceladonite
lilalite (s)	lepidolite
Lilalith (s)	lepidolite
lime mica (s)	margarite
lithia mica (s)	lepidolite, zinnwaldite
Lithioneisenglimmer (s)	zinnwaldite
Lithionglimmer (s)	lepidolite
Lithionit (s)	lepidolite
lithionite (s)	lepidolite
lithionitesilicat (s)	lepidolite
lithium muscovite (s)	trilithionite, lithian muscovite
lithium phengite (v)	lithian muscovite
macrolepidolite (s)	lepidolite
magnesia mica (s)	phlogopite
magnesiomargarite (v)	clintonite
magnesium sericite (v)	magnesian illite
manganese mica (v)	biotite
manganese muscovite	manganoan muscovite
manganglauconite (v)	glauconite
mangan-muscovite	manganoan muscovite
manganmuscovite	manganoan muscovite
manganophyll (v)	biotite
manganophyllite (v)	biotite
manganphlogopite (v)	manganoan phlogopite
margarodite	muscovite
Marienglas	muscovite
mariposite (s)	chromian phengite, chromian muscovite
marsjatskite	glauconite
marsyatskite	glauconite
meroxene (v)	biotite
metasericite	muscovite
microlepidolite	lepidolite
monrepite (s)	ferrian annite
Na brittle mica (s)	preiswerkite
Na-eastonite (s)	preiswerkite
nacrite (Thomson) (s)	muscovite
natrium illite (s)	brammallite
natro-alumobiotite (v)	biotite, sodian siderophyllite
natro-ferrophlogopite (v)	biotite, sodian phlogopite
natronbiotite (v)	biotite
natronphlogopite (v)	sodian phlogopite
natronmargarite (s)	calcic paragonite, calcic ephesite
nickel phlogopite (v)	nickeloan phlogopite
oblique mica	muscovite
odenite	biotite
Odinit	biotite
Odith	biotite
oellacherite	barian muscovite
oncophyllite	muscovite
Onkophyllit	muscovite
paucilithionite (s)	trilithionite
pearl-mica (s)	margarite
Perlglimmer (s)	margarite
picrophengite (v)	magnesian muscovite

Table 5. Continued.

poly-irvingite (v)	lepidolite
potash margarite (v)	margarite
potash mica	muscovite
pregrattite (s)	paragonite
protolithionite (v)	zinnwaldite, lithian annite, lithian siderophyllite
pyncophyllite	fine-grained muscovite or illite
Pyknophyllit	fine-grained muscovite or illite
Rabenglimmer (s)	zinnwaldite
Rhombenglimmer (v)	phlogopite, biotite
rhombic mica (v)	phlogopite, biotite
sandbergite	barian muscovite
sarospatakite	illite
scale stone (s)	lepidolite
schemikite	muscovite
Schuppenstein (s)	lepidolite
seladonite (s)	celadonite
seybertite (v)	clintonite
shilkinite (v)	ferroan muscovite, ferroan illite
siderischer-Fels-Glimmer (s)	lepidolite
skolite (s)	glauconite
soda glauconite (v)	glauconite
soda margarite (s)	calcic paragonite, calcic ephesite
soda mica (s)	paragonite
sodium illite (s)	brammallite
sodium phlogopite (s)	aspidolite
sterlingite	muscovite
svitalskite (v)	celadonite
taeniolite (s)	tainiolite
talcite	muscovite
titanbiotite (v)	biotite
Titanglimmer (v)	biotite
titanmica (v)	biotite
titanobiotite (v)	biotite
valuevite (v)	clintonite
vanadium mica (s)	roscoelite
Vanadinglimmer (s)	roscoelite
verdite	chromian muscovite
Verona earth (s)	celadonite
veronite (s)	celadonite
voron'ya slyuda (v)§	zinnwaldite, lithian annite, lithian siderophyllite
walouewite (v)	clintonite
waluewite (v)	clintonite
Walujewit (v)	clintonite
wodanite (v)	biotite
wotanite (v)	biotite
xanthophyllite (v)	clintonite
zweiaxiger Glimmer	muscovite

† The mineral "gebhardtite" has the formula $Pb_8O(As_2O_5)_2Cl_6$.

‡ Also used for hematite.

§ "Raven mica" or "crow mica" in Russian.

resented an old description of what was in more recent years referred to as "sodium phlogopite" (Schreyer et al. 1980). It must be pointed out that no one ever applied formally for the mineral name "sodium phlogopite".

Brammallite

A reasoning similar to that concerning "illite" has led the Mica Subcommittee to list it as a series name. A more precise end-member nomenclature might develop at a later time.

Divisions within the Interlayer-deficient Micas

In the subgroup of interlayer-deficient micas, some divisions comply with Nickel (1992), but some do not. The non-50% limits adopted by the Mica Subcommittee as divides between volumes in interlayer-deficient micas are essentially those of Bailey et al. (1979).

Illite

This name has been used relatively vaguely, and the Mica Subcommittee found it suitable as a series name

Table 6. Ill-defined materials and mixtures. Usage of these names is discouraged unless the ill-defined micas are substantiated by new research.

achlusite	a sodium mica?
antrophyllite	a mica?
avalite	chromian illite or a mineral mixture
baddeckite	muscovite & hematite
bardolite	interstratified biotite & vermiculite?
basonite	interstratified biotite & vermiculite
bastonite	interstratified biotite & vermiculite
bravaisite	illite & montmorillonite
buldymite	biotite & vermiculite or interlayer-deficient biotite
caswellite	mica & manganoan andradite
cataspilite	alteration product with dominant muscovite
catlinite	muscovite & pyrophyllite
chacaltaite	illite pseudomorph after cordierite
cymatolite	muscovite & albite
dudleyite	a smectite?
ekmanite	a smectite?
epichlorite	an altered chlorite?
epileucite	muscovite & K-feldspar pseudomorph after cordierite
episericite	illite?
eukamptite	altered biotite
euphyllite	paragonite & muscovite or paragonite
gigantolite	muscovite & cordierite
hallerite	paragonite & lithian muscovite
helvetan	decomposed biotite
hexagonal mica	a mica?
hydrophlogopite	interstratified phlogopite & vermiculite
hydropolythionite	an altered lepidolite?
iberite	altered cordierite & zeolite
ivigitite	muscovite? sodian ferruginous mica?
kryptotile	probably not a mica
ledikite	interstratified biotite & vermiculite
lesleyite	a variety of margarite or a mineral mixture
leverrierite	probably not a mica
mahadevite	an Al-rich biotite?
Melanglimmer	biotite? stilpnomelane? cronstedtite?
metabiotite	weathering product of biotite
Mg-illite-hydromica	interstratified phlogopite & vermiculite
minguetite	interstratified biotite & vermiculite?
oncosine	muscovite ± quartz ± other phases
Onkosin	muscovite ± quartz ± other phases
onkosine	muscovite ± quartz ± other phases
pattersonite	interstratified biotite & vermiculite
philadelphite	decomposition product of biotite, a vermiculite?
pholidolite	phlogopite? saponite?
pinite	pseudomorph mostly of mica after cordierite, nepheline, or scapolite
pseudobiotite	interstratified biotite & vermiculite or interlayer-deficient biotite
pterolite	decomposition product of hornblende consisting of mica & alkali pyroxene
rastolyte	altered biotite or interlayer-deficient biotite
rubellan	altered biotite or interlayer-deficient biotite, vermiculite?
sericite	fine-grained aggregate of mica-like phases
spodiophyllite	possibly a mica related to tainiolite
trioctahedral illite	interstratified biotite & vermiculite
uniaxial mica	a biotite?
vaalite	a vermiculite?
volgtite	weathering product of biotite or interlayer-deficient biotite
waddoite	a mica?

for a relatively large volume in compositional space, as a counterpart to "glaucinite".

Interlayer-deficient Micas versus Hydromicas

The Mica Subcommittee was unable to find any "hydromica" that has an excess of water over the

equivalent of (OH, F)₂ and could not be interpreted as a mixed-layer structure (such as biotite-vermiculite, illite-smectite). At the same time, all micas described as "hydromicas" exhibit a deficiency in the interlayer cation position. Accordingly, the Mica Subcommittee voted to abandon the subgroup name

Table 7. Names formerly or erroneously used for micas.†

agalmatolite	pyrophyllite or a mixture with dominant pyrophyllite
allevardite	rectorite
bannisterite	related to islandlike modulated 2:1 layer silicates
Bildstein	pyrophyllite or a mixture with dominant pyrophyllite
chalcodite	stilpnomelane
Fe muscovite	invalid name, hypothetical end member
ferrimuscovite	invalid name, hypothetical end member
ferrophengite	invalid name, hypothetical end member
ferrostilpnomelane	stilpnomelane
ganophyllite	modulated 2:1 layer silicate
hydrobiotite	regular 1:1 interstratification of biotite & vermiculite
iron muscovite	invalid name, hypothetical end member
kerrite	vermiculite
maconite	related to vermiculite
manandonite	boron-rich serpentine
pagodite	pyrophyllite or a mixture with dominant pyrophyllite
parsettensite	modulated 2:1 layer silicate
stilpnochlorane	nonttronite
tarasovite	regular 3:1 interstratification of dioctahedral mica & smectite

† Names in the left column are not to be necessarily considered discredited.

“hydromicas” and replace it with “interlayer-cation-deficient micas” or, in an abbreviated form, “interlayer-deficient micas”.

Phengite

Phengite was elevated to a series name for solid solutions between muscovite, aluminoceladonite and celadonite.

Species that are not End Members

The Mica Subcommittee voted to consider as end members only formulas that are stoichiometric on the scale of the asymmetric part of the unit cell. This principle ruled out a number of micas; the Mica Subcommittee decided it would be best to refer to nonstoichiometric micas that have a fairly constant and recurring composition as “species that are not end members”. The micas so designated are montdorite, trillithionite and wonesite.

Synonyms (s) and Varieties (v)

The list is based on tabulations of Heinrich et al. (1953) and Hey (1962, 1963), modified and supplemented. Labels “(s)” or “(v)” could only be attached where there was sufficient information. If a series name appears to the right of a variety rather than a species name, it is because no more precise information is available.

Tainiolite

The Mica Subcommittee prefers the original spelling “tainiolite” to “taeniolite”. The spelling of Flink (1899) was based on Greek words ταινία (a band or strip) and λίθος (a stone). It should be noted that the Russian spelling has always been *тайниолит*.

Tetra-ferri-annite

Inasmuch as Wahl's (1925) analyses do not make the case for ⁴Fe(III) strong enough, his “monrepite” was rejected as an end member, with “tetra-ferri-annite” taking its place. Parallel with it is the name “tetra-ferriphlogopite”.

ACKNOWLEDGMENTS

Since its establishment in 1976, the Mica Subcommittee benefited from, and is indebted for, ideas offered by a large number of mineralogists; there were so many of them that they cannot be acknowledged individually. The votings on the nomenclature and the handling of associated problems was facilitated thanks to the expertise of J. D. Grice and W. D. Birch. We thank C. V. Guidotti and R. F. Martin for valuable final comments on the text and tables.

REFERENCES

- Bailey SW. 1984. Classification and structures of the micas. In: Bailey SW, editor. *Rev Mineral* 13. Micas. Washington, DC. Mineral Soc Am. p 1–12.
- Bailey SW, Brindley GW, Kodama H, Martin RT. 1979. Report of the Clay Minerals Society Nomenclature Committee. *Clays Clay Miner* 27:238–239.
- Bailey SW, Frank-Kamenetskii VA, Goldsztaub S, Kato A, Pabst A, Schulz H, Taylor HFW, Fleischer M, Wilson AJC. 1977. Report of the International Mineralogical Association (IMA)-International Union of Crystallography (IUCr) Joint Committee on Nomenclature. *Acta Crystallogr* A33:681–684.
- Baronnet A. 1980. Polytypism in micas: A survey with emphasis on the crystal growth aspect. In: Kaldis E, editor. *Current Topics Mater Sci* 5. Amsterdam: North-Holland Publ Co. p 447–548.
- Đurovič S. 1981. OD-Charakter, Polytypie und Identifikation von Schichtsilikaten. *Fortschr Mineral* 59:191–226.
- Flink G. 1899. Tainiolite. In: Flink G, Bøggild OB, Winther C. 1899. *Mineraler fra Juliønehaab indsamlede af G. Flink 1897*. *Medd Grøn* 24:115–120.
- Foster MD. 1960. Interpretation of the composition of trioctahedral micas. *US Geol Surv Prof Pap* 354-B:11–48.
- Guinier A, Bokij GB, Boll-Dornberger K, Cowley JM, Đurovič S, Jagodzinski H, Krishna P, de Wolff PM, Zvyagin BB, Cox DE, Goodman P, Hahn Th, Kuchitsu K, Abrahams SC. 1984. Nomenclature of polytype structures. Report of the International Union of Crystallography Ad-Hoc Committee on the Nomenclature of Disordered, Modulated and Polytype Structures. *Acta Crystallogr* A40:399–404.
- Heinrich EW, Levinson AA, Levandowski DW, Hewitt CH. 1953. Studies in the natural history of micas. *Project M978*. Ann Arbor: Eng Res Inst, Univ of Michigan. 241 p.
- Hey MH. 1962. An index of mineral species & varieties arranged chemically. London: British Museum. 728 p.
- Hey MH. 1963. Appendix to the second edition of An index of mineral species and varieties arranged chemically. London: British Museum. 135 p.

- von Kobell F. 1869. Ueber den Aspidolith, ein Glied aus der Biotit- und Phlogopit-Gruppe. Sitzungsber königl bayer Akad Wiss München Jg 1869 Bd I:364–366.
- Nickel EH. 1992. Nomenclature for mineral solid solutions. *Am Mineral* 77:660–662.
- Nickel EH. 1993. Standardization of polytype suffixes. *Am Mineral* 78:1313.
- Rimsaite J. 1970. Structural formulae of oxidized and hydroxyl-deficient micas and decomposition of the hydroxyl group. *Contrib Mineral Petrol* 25:225–240.
- Ross M, Takeda H, Wones DR. 1966. Mica polytypes: Systematic description and identification. *Science* 151:191–193.
- Schreyer W, Abraham K, Kulke H. 1980. Natural sodium phlogopite coexisting with potassium phlogopite and sodian aluminian talc in a metamorphic evaporite sequence from Derrag, Tell Atlas, Algeria. *Contrib Mineral Petrol* 74: 223–233.
- Starkl G. 1883. Ueber neue Mineralvorkommnisse in Oesterreich. *Jahrb kaiserl-königl geol Reichsanst Wien* 33:635–658.
- Stevens RE. 1946. A system for calculating analyses of micas and related minerals to end members. *US Geol Surv Bull* 950:101–119.
- Takeda H, Ross M. 1995. Mica polytypism: Identification and origin. *Am Mineral* 80:715–724.
- Takeda H, Sadanaga R. 1969. New unit layers for micas. *Mineral J (Japan)* 5:434–449.
- Wahl W. 1925. Die Gesteine des Wiborger Rapakiwgebietes. *Fennia* 45:83–88.
- Zvyagin BV. 1964. Электроннография и структурная кристаллография глинистых минералов. Moscow: Nauka. 282 p.
- Zvyagin BV, Vrublevskaya ZV, Zhukhlistov AP, Sidorenko OV, Soboleva SV, Fedotov AF. 1979. Высоковольтная электроннография в исследовании слоистых минералов (High-voltage electron diffraction in the study of layered minerals). Moscow: Nauka. 224 p.